Public reporting burd gathering and mainti-collection of informa Davis Highway, Suite

# AD-A281 123

**AGE** 

Form Approved OMB No. 0704-0188

response, including the time for reviewing instructions, searching existing data sources shown as the comments regarding this Syrden estimate or any other aspect of this diguarters Services, Directorate for Information Operations and Reports, 1215 Jeffersor Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503

1. AGENCY US

6. AUTHOR(S)

6/28/94

3. REPORT TYPE AND DATES COVERED

1/1/93 - 6/28/94

4. TITLE AND SUBTITLE

Log-x<sup>2</sup> Distribution of Correlation Times Revisted

5. FUNDING NUMBERS

PE-N0014-91

PR-1274

Robert D. O'Connor and Frank D. Blum

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

University of Missouri-Rolla Department of Chemistry Rolla, MO 65401

ATTN: Frank D. Blum

PERFORMING ORGANIZATION REPORT NUMBER

UMR-FDB-39

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Office of Naval Research - Code 5000 Chemistry Division 800 Quincy Street

Arlington, VA 22217 ATTN: Kenneth J. Wynne
11. SUPPLEMENTARY NOTES JUL 06 1994

10. SPONSORING/MONITORING AGENCY REPORT NUMBER

For publication in Macromolecules

12a. DISTRIBUTION / AVAILABILITY STATEMENT

Unlimited - Approved for unlimited public release

13. ABSTRACT (Maximum 200 words)

The  $\log-\chi^2$  distribution of correlation times and its application to polymer systems are examined. It is found that the original mean correlation-time parameter,  $\tau_0$ , (Macromolecules, 1973, 6, 882) does not represent the true mean of the distribution. A properly parameterized log- $\chi^2$  distribution and function relating the original  $\tau_0$  and width parameters, p and b, to the true mean are derived. Fitting of both the original  $\log -\chi^2$ , corrected  $\log -\chi^2$ , and  $\log$ -normal distribution to experimental data is discussed and the log-normal distribution being proposed as an alternative. Interpretations of NMR data from polymer/solvent systems can be different for the  $\log \gamma^2$  and  $\log \gamma$ normal distributions. Due to its better defined moments, the log-normal's results are believed to be more physically realistic when large widths are required.

	NMR, polymers, mo		15. NUMBER OF PAGES 14			
					16. PRICE CODE	
17.	SECURITY CLASSIFICATION OF REPORT	N 18. SECURITY CLAS OF THIS PAGE	SIFICATION 19.	SECURITY CLASSIFI OF ABSTRACT	CATION 20. LIMITATION C	F ABSTRACT

Unclassified

·\$\ 7540-01-280-5500

Unclassified

Standard Form 298 (Rev. 2-89) Prescribed by ANSI Std. 239-18 298-12

Unclassified

### OFFICE OF NAVAL RESEARCH

Grant N00014-91-J-1274

R&T Code 413m005---04

Technical Report # UMR-FDB-39

 $\text{Log }\chi^2$  Distribution of Correlation Times Revisited

by

Robert D. O'Connor and Frank D. Blum


Department of Chemistry and Materials Research Center University of Missouri-Rolla Rolla, MO 65401

(314) 341-4451

Prepared for Publication in

Macromolecules

June 28, 1994



Reproduction in whole, or in part, is permitted for any purpose of the United States Government.

This document has been approved for public release and sale: its distribution is unlimited.

94 7 5 145

#### **ABSTRACT**

The  $\log -\chi^2$  distribution of correlation times and its application to polymer systems are examined. It is found that the original mean correlation-time parameter,  $\tau_0$ , (Macromolecules, 1973, 6, 882) does not represent the true mean of the distribution. A properly parameterized  $\log \chi^2$  distribution and function relating the original  $\tau_0$  and width parameters, p and b, to the true mean are derived. Fitting of both the original  $\log -\chi^2$ , corrected  $\log -\chi^2$ , and  $\log$ -normal distribution to experimental data is discussed and the  $\log$ -normal distribution being proposed as an alternative. Interpretations of NMR data from polymer/solvent systems can be different for the  $\log -\chi^2$  and  $\log$ -normal distributions. Due to its better defined moments, the  $\log$ -normal's results are believed to be more physically realistic when large widths are required.

Often, definitive models for molecular motion do not exist or fail to give reasonable results. And, as an approximation, an exponential decay of correlation with a distribution of correlation times is used as the correlation function. Such distributions prove very useful, especially for polymers and polymer solutions, at describing and quantifying the dynamics. 1-8

Heatley<sup>8</sup> has summarized the successes and failures of several of the distributions used to describe polymer dynamics. Of these, the asymmetric  $\log_2 \chi^2$  distribution has had good success in fitting data from a broad range of techniques including NMR, ESR, and dielectric studies.<sup>1,2,5,8</sup> We have found that the use of the  $\log_2 \chi^2$  distribution may occassionally yield parameters which should not be compared from system to system. In some cases, a proper comparison can be made with the application of a correction factor. For example, the application of the  $\log_2 \chi^2$  distribution, as proposed in the literature,<sup>1</sup> to NMR relaxation data of toluene in polystyrene generated a slower mean rotational correlation time for pure toluene than it did for motionally hindered toluene near polystyrene at the same temperature. It also yielded unphysical results in a dynamics study of poly(*iso*-propyl acrylate) (PIPA).<sup>7</sup> In that study, the mean correlation time predicted by the log- $\chi^2$  distribution had little correlation with polymer concentration, often being faster for more concentrated solutions than for less concentrated ones at the same temperature. Other models employed to quantify the PIPA system suffered similar problems. After examining the  $\log_2 \chi^2$  distribution, we found that the parameter  $\tau_0$ , previously interpreted as the mean correlation time, is not the true mean, but rather a scaling factor which can be related to the true mean.

A normalized, scaled, base b  $\log -\chi^2$  distribution,  $F^{\chi}(\tau_c; b, p, \theta)$ , has the form of:

$$F^{\chi}(\tau_{c}; b, p, \theta) = \frac{1}{\theta} \frac{\left(\frac{p}{\ln(b)}\right)^{p}}{\Gamma(p)} \left(\ln(\frac{\tau_{c}}{\theta} + 1)\right)^{p-1} \left(\frac{\tau_{c}}{\theta} + 1\right)^{-(p/\ln(b) + 1)} \qquad \text{for } 0 \le \tau_{c} \le \infty$$
 (1)

with  $\tau_c$ , b, p,  $\theta$ , and  $\Gamma$  the correlation time, numerical base, width parameter, scaling parameter, and gamma function, respectively. The superscript  $\chi$  denotes the log- $\chi^2$  distribution. The

parameter b is often fixed at 1000, but it could be replaced with e, the natural base. The mean,  $\tau_0^{\chi}(b,p,\theta)$ , of  $F^{\chi}(\tau_c;b,p,\theta)$  is:

$$\tau_0^{\chi}(b,p,\theta) = \int_0^\infty \tau_c F^{\chi}(\tau_c; b,p,\theta) d\tau_c = \theta \left[ \left( \frac{p}{p-\ln(b)} \right)^p - 1 \right]$$
 (2)

Experiments often probe the dynamics through the Fourier transform of the correlation function or spectral density,  $J(\omega)$ . For a distribution,  $F(\tau_c)$ , of exponentially decaying correlation times,  $J(\omega)$  is:

$$J(\omega) = \int_0^\infty \frac{2 F(\tau_c) \tau_c}{1 + \omega^2 \tau_c^2} d\tau_c$$
 (3)

where  $\omega$  and  $\tau_c$  are the frequency and correlation time, respectively.  $F^{\chi}(\tau_c; b, p, \theta)$  could be used in equation (3) and the mean correlation time calculated from equation (2) after determining the parameters b, p, and  $\theta$ . However, transforming the distribution and spectral density to a reduced correlation time will allow a more direct comparison with the original work<sup>1</sup> and eliminate the need for equation (2) as the scaling parameter,  $\theta$ , will be replaced by a mean correlation-time parameter,  $\tau_0$ .

With the transformation  $\tau_r = \tau_c/\tau_0^{\chi}(b,p,\theta)$  applied to  $F^{\chi}(\tau_c;b,p,\theta)$ , the  $\log -\chi^2$  distribution of reduced correlation times,  $G^{\chi}(\tau_r;b,p)$ , is:

$$G^{\chi}(\tau_{r}; b,p) = \frac{\left(\frac{p}{\ln(b)}\right)^{p}}{\Gamma(p)} \tau_{0}^{\chi}(b,p,1) \left(\ln(\tau_{r} \tau_{0}^{\chi}(b,p,1) + 1)\right)^{p-1} \left(\tau_{r} \tau_{0}^{\chi}(b,p,1) + 1\right)^{-(p/\ln(b) + 1)}$$
(4)

For simplicity,  $\theta$  is set to one in the argument as the transformation eliminates any  $\theta$  dependence. Similarly,  $J(\omega)$  becomes:

$$J(\omega) = \int_0^\infty \frac{2 G^{\chi}(\tau_r; b, p) \tau_r \tau_0}{1 + \omega^2 \tau_r^2 \tau_0^2} d\tau_r$$
 (5)

where  $\tau_0$  has replaced  $\tau_0^{\chi}(b,p,\theta)$  and, consequently, represents the true mean of the distribution.

If  $F^{\chi}(\tau_c; b,p,\theta)$  had been scaled by the parameter  $\tau_0$ , as in reference (1), instead of  $\tau_0^{\chi}(b,p,\theta)$ ,  $\tau_0$  of equation (5) would not be the true mean, but a scaling parameter. The mean correlation time could then be calculated from:

$$\langle \tau_c \rangle = \int_0^\infty \tau_c \ F^{\chi}(\tau_c; b, p, \theta) \ d\tau_c = \tau_0 \int_0^\infty \tau_r \ G^{\chi}(\tau_r; \tau_0, b, p, \theta) \ d\tau_r$$
 (6)

where  $G^{\chi}(\tau_r; \tau_0, b, p, \theta)$  is  $F^{\chi}(\tau_c; b, p, \theta)$  scaled about the *parameter*  $\tau_0$ . Being scaled about  $\tau_0^{\chi}(b, p, \theta)$  simplifies matters by cancelling any previous scaling and making the mean of  $G^{\chi}(\tau_r; b, p) = 1$  and, so,  $\langle \tau_c \rangle = \tau_0$ .

For comparison, the spectral density (equation (5)) can be but into a form similar to equation (25) of reference (1):

$$J(\omega; \tau_0, b, p) = \int_0^\infty \frac{2 \chi^2(s, p) [e^{s}-1] \tau_0}{\left[ \left( \frac{p}{p-\ln(b)} \right)^p - 1 \right] \left[ 1 + \omega^2 \tau_0^2 \left( [e^{s}-1] / \left( \frac{p}{p-\ln(b)} \right)^p - 1 \right] \right)^2} ds$$
 (7)

where p, b, and  $\omega$  are as defined previously, s is an integration variable,

$$\chi^{2}(s,p) = \frac{p^{p}}{\Gamma(p)} s^{p-1} e^{-s p}$$
 (8)

and  $\tau_0$  is the mean correlation time of the distribution.

The relationship between the true mean,  $\tau_0$ , of equations (5) and (7) and the originally reported mean,  $\tau_0^{org}$ , can be calculated from equation (6) and is:

$$\tau_0 = \tau_0^{\text{org}} \frac{\left(\frac{p^{\text{org}}}{p^{\text{org}} - \ln(b^{\text{org}})}\right)^{p^{\text{org}}} - 1}{b^{\text{org}} - 1}$$
(9)

where the superscript org indicates parameters that were fitted from the original distribution. Depending on b and p, this could be a large correction and, consequently, responsible for the  $\log -\chi^2$ 's previously reported unphysical behavior. Also, this equation and the distribution itself are only valid for  $p > \ln(b)$  where the distribution is normalizable. The possible limitations of the distribution and its dependencies on p and b are clarified by examining the moments of  $G^{\chi}(\tau_r; b, p)$  which are:

$$\langle \tau_r^n \rangle = \int_0^\infty \tau_r^n G^{\chi}(\tau_r; b, p) d\tau_r = \sum_{i=0}^n \binom{n}{i} \left(-1\right)^{n-i} \left(\frac{p}{p-i \ln(b)}\right)^p \left(\left(\frac{p}{p-\ln(b)}\right)^p - 1\right)^{-n}$$
(10)

where  $\binom{n}{i}$  is the binomial coefficient. The original distribution has a similar form for its moments. For large values of p, the moments are essentially independent of b. For the intermediate values,  $\ln(b)$  scales p to smaller values, making the distribution wider for a given  $p/\ln(b)$  ratio. Finally, for small values of p, the dependence is unclear as the moments are infinite. This behavior suggests that the natural base e should work as well as any other, i.e. 1000, as long as p is not restricted to integer values. Indeed, with non-integer p values, all data tested fit equally well and with the same predicted  $\tau_0$  using either e or 1000 as the base.

To test the corrected  $\log - \chi^2$  distribution's ability to fit polymer data and yield physically meaningful results, we used it to fit four data sets: polystyrene, polyisoprene, and polybutadiene  $^{13}\text{C T}_1\text{-T}_2$  (20.6 MHz) data from the original paper¹; polyisoprene  $^{13}\text{C T}_1$  (20.1 and 100.6 MHz) data⁵; poly(iso-propyl acrylate)-d in chloroform  $^2\text{H T}_1\text{-T}_2$  (13.8 MHz) $^7$  data; and, toluene- $d_5$  in polystyrene  $^2\text{H T}_1\text{-T}_2$  (30.7 MHz) data. $^6$  These systems represent a wide variety of polymer dynamics, namely bulk polymer dynamics, solution state polymer dynamics, and solvent dynamics in polymer solutions.

For the polymer data in the original paper, the mean correlation times,  $\tau_0$ 's, from both the original and modified  $\log -\chi^2$  seem physically reasonable for polystyrene in o-dichlorobenzene and bulk polyisobutene. However, the original distribution yielded an unusually fast  $\tau_0$  of 0.1 ns for bulk polybutadiene. Using equation (9), this  $\tau_0$  became 5 ns, the same value fit from the modified distribution. This seems more reasonable. In general, the modified  $\log -\chi^2$  distribution generates larger  $\tau_0$ 's than the original. But, with the use of equation (9) both distributions yield the same  $\tau_0$ , with smaller values of p requiring larger corrections. These results are typical of all the data fit in this paper.

Unlike  $T_1$ - $T_2$  data investigated, both the modified and original (in conjuction with equation (9))  $\log -\chi^2$  distributions generate unrealistically  $\log \tau_0$ 's from the polyisoprene  $^{13}$ C  $T_1$  data. Table I lists the results from the  $^{13}$ C data. The reason the  $\log -\chi^2$  distribution fails for the  $^{13}$ C data is not clear. It may linked to its undefined moments and that the  $^{13}$ C data only samples the distribution in the MHz region. As can be seen from Table I, the modified  $\log -\chi^2$  compares well until p becomes less than  $2*\ln(b)$  below which only the  $\log -\chi^2$ 's first moment exists. For these values of p, the distribution's tail is poorly parameterized and large correlation times may be unduely weighted. To successfully fit data to such a distribution, some constraints on the tail, as the zero frequency  $T_2$  data imposes, would probably help give more reasonable results.

As an alternative to low frequency data, the log-normal distribution might be used. Its moments exist; so, its tail and skew are well defined. In general, it has simple dependencies on its parameters (easy to fit); is well behaved with well defined moments; and, is more skewed than the  $\log -\chi^2$ . It also affords a simple physical interpretation of the underlying processes. 10.11.12 The distribution of reduced correlation times,  $G(\tau_i; \sigma)$ , for the log-normal distribution is:

$$G(\tau_{\mathbf{r}}; \sigma) = \frac{1}{\sqrt{\pi} \sigma \tau_{\mathbf{r}}} e^{-(\ln(\tau_{\mathbf{r}})/\sigma + \sigma/4)^2}$$
(11)

which would replace  $G^{\chi}(\tau_r; b,p)$  in equation (5). Its second moment is:

$$\langle \tau_i^2 \rangle = e^{\sigma^2/2} \tag{12}$$

and its mean is one, as expected from the scaling.

The log-normal distribution fit both the  $T_1$ - $T_2$  and  $^{13}$ C  $T_1$  data discussed ealier with vanishing error and few iterations of the fitting algorithm.  $^{13}$  For these data, except for where log- $\chi^2$  failed, the  $\tau_0$ 's were essentially identical between the modified  $\log -\chi^2$  and the log-normal, differing from the original  $\log -\chi^2$  according to equation (9). As mentioned previously, the predicted magnitudes and trends of the  $\tau_0$ 's were more realistic than those of the original  $\log -\chi^2$  and, for the PIPA data, also more realistic than other models employed (compare Figure 1 to similar plots in reference (7)). That is, the  $\tau_0$ 's increased with increasing polymer concentration or decreasing temperature, realistic in an intuitive sense.

For reference (5), the main difference between the log-normal and the original  $\log -\chi^2$  is that the log-normal predicts a higher apparent activation energy for the high temperature data and a 10 fold increase in  $\tau_0$  at low temperatures. As in the reference (5), the NOEF's were not used in the fitting procedure. They offer an independent test of each distribution's predictive ablilty. Unfortunately, the calculated NOEF's follow the experimental values for all the distributions and no distinction can be made. For extremely broad distributions, however, the log-normal has a limiting,  $\tau_0$  independent, NOEF value of 1.33 compared to the  $\log -\chi^2$ 's value of 0.9 (at 20 Mhz). This increase is presumably due to the larger skew of the log-normal distribution. None of the experimental data required broad enough distributions to test this difference.

In conclusion,  $\tau_0$  of the original  $\log -\chi^2$  distribution is a scaling parameter which is often, but not always, representative of the mean. Comparisons and predicted trends may be on different scales unless a correction to the true mean (equations (6) and (9)) is made. Modifying the distribution yields a new distribution in which  $\tau_0$  is the true mean. However, both the original and modified  $\log -\chi^2$  distribution have limited use as their moments can be ill-defined and careful sampling of the frequency space is required. We prefer the log-normal distribution as it is better skewed, and has well defined moments and simple derivatives. Its ability to fit and give physically

reasonable results from low and high frequency  $T_1$ - $T_2$  data as well as soley high frequency  $T_1$  data indicates that it may be useful where the log- $\chi^2$  appears unphysical. 6,7,8,14,15

Acknowledgement. The authors thank the Office of Naval Research for financial support of this work. They also acknowledge the helpful suggestions of Professor Jake Schaefer (Washington University).

#### References and Notes

- (1) Schaefer, J. Macromolecules 1973, 6, 882.
- (2) Denault, J.; Morese-Seguela, B.; Seguela, R.; Prud'homme, J. Macromolecules 1990, 23, 4658.
- (3) Asakura, T. Macromolecules 1983, 16, 786.
- (4) Wittebort, R. J.; Szabo, A.; Gurd, F. R. N. J. Am. Chem. Soc. 1980, 102, 5723.
- (5) Denault, J.; Prud'homme, J. Macromolecules 1989, 22, 1307.
- (6) naNagara, B.; O'Connor, R.; Blum, F. D. J. Phys. Chem. 1992, 96, 6417.
- (7) Blum, F. D.; Durairaj, B.; Padmanabhan, A. S. Macromolecules 1984, 17, 2837.
- (8) Heatley, F. Ann. Rep. NMR Spec. 1986, 17, 179, and references therein.
- (9) Aitchison, J.; Brown, J. A. C. The Lognormal Distribution Cambridge University, 1957.
- (10) Montroll, E. W.; Schlesinger, M. F. In *The Mathematics and Physics of Disordered Media*; Hughes, B. D.; Ninham, B. W. Eds.; Lecture Notes in Mathematics 1035; Springer Verlag, 1983; p 134.
- (11) Rössler, E.; Taupitz, M.; Börner, K.; Schultz, M.; Vieth, H. M. J. Chem. Phys. 1990, 92, 5847.
- (12) Pfeifer, H. In NMR Basic Principle and Progress; Diehl, P.; Fluck, E.; Kosfeld, R. Eds; Springer Verlag 1972; p 53.
- (13) IMSL's numerical integration and modified Levenberg-Marguardt non-linear minimization routines were used to calculate and fit all data. Typical errors, defined as:

$$\%error = \sum_{i=1}^{2} \left( \frac{T_i^{exp} - T_i^{calc}}{T_i^{exp}} \right)^2$$

were  $10^{-6}$  for both Schaefer's original distribution and the modified  $\log -\chi^2$  and  $10^{-30}$  for the log-normal. For all  $\log -\chi^2$ 's, the number of iterations ranged from 20 to 2000, depending on the quality of the initial guesses. For the log-normal, the number of iterations was always less than 50, independent of the initial guess.

- (14) Heatley, F.; Cox, M. K. Polymer 1977, 18, 225.
- (15) Jones, A. A.; Lubianez, R. P. Macromolecules 1978, 11, 126.

Table I Fits to the  $C_1$  methylene  $^{13}C$   $T_1$  data of reference (5) ( $M_n=7$  kg/mol) (b=1000)

			log-χ <sup>2</sup> <sub>org</sub> a		log-χ <sub>o</sub>	log- $\chi^2_{org}^b$		$\log - \chi_{\text{mod}}^2$		log-normal <sup>d</sup>	
T (K)	T <sub>1</sub> (100MHz)	T <sub>1</sub> (20MHz)	τ <sub>0</sub> (ns)	p	τ <sub>0</sub> (ns)	p	τ <sub>0</sub> (ns)	p	τ <sub>0</sub> (ns)	σ	
293	0.152	0.035	2.00	7	1.90	7.3	340*10 <sup>3</sup>	7.5	20.0	3.45	
303	0.156	0.043	1.00	7	0.67	8.0	5500	8.0	7.10	3.36	
313	0.168	0.053	0.40	8	0.31	9.4	71.2	9.5	3.30	3.27	
323	0.185	0.068	0.17	11	0.17	11.5	6.48	11.5	1.40	3.07	
333	0.210	0.090	0.10	14	0.10	14.0	1.41	14.0	0.660	2.86	
343	0.239	0.135	0.073	24	0.076	23.3	0.272	23.5	0.240	2.25	
353	0.275	0.192	0.062	34	0.064	35.7	0.139	35.7	0.130	1.80	
363	0.323	0.255	0.053	45	0.054	45.6	0.097	45.6	0.095	1.57	
373	0.378	0.310	0.043	47	0.044	45.7	0.079	45.7	0.078	1.58	
E <sub>a</sub> -High Temp. (kJ)			18.	6	19	.6	43.	6	38	.7	
E <sub>a</sub> -Low Temp. (kJ)			63.	0	59	.2	257	7e	68	.5	

<sup>&</sup>lt;sup>a</sup> fit by Denault and Prud'homme using original log- $\chi^2$ ;

b recalculated data using original  $\log -\chi^2$  and non-integer p's;

<sup>.</sup> c modified log- $\chi^2$ , equation (4);

d log-normal distribution, equation (11);

e see text for explanation.

## Figure Caption

Figure 1.  $\tau_0$  values from the log-normal distribution's fit to <sup>2</sup>H T<sub>1</sub> and T<sub>2</sub> data (reference (7)) as a function of temperature and PIPA concentration. The curves drawn are for visual clarification.

